



THE MOST RELIABLE WELDING®

HOFFMAN ARC CO., LTD

QUALITY CERTIFICATE OF WELDING CONSUMABLE

Type	Norm	Brand Name	Part #	Diameter	Lot No.	Manufactured Date	Date of Issue
E7018	AWS A5.1/A5.1M-2012	SINNVOLL	6001801	3/32" (2.4mm)	19-1243	Shown on Package	29 - 09 - 2019

Mechanical Properties of Deposited Metal				Chemical Composition of Deposited Metal (%)						
Item		Requirement	Actual Result	Element	Requirement	Actual Result	Element	Requirement	Actual Result	
Tensile Test	Yield Strength Rel(MPa)	Min 400	465	C	Max. 0.15	0.069	Mo	Max. 0.30	0.029	
	Tensile Strength Rm(MPa)	Min. 490	580	Si	Max. 0.75	0.56	V	Max. 0.08	0.0059	
	Elongation A5 (%)	Min 22	26.5	Mn	Max. 1.60	1.35	--	--	--	
Impact Test	Impact Temp (°C)	-30	-30	S	Max. 0.035	0.014	--	--	--	
	Impact. Absorbed Energy (J)	Min. 27	98 115 100	P	Max. 0.035	0.018	--	--	--	
X-Ray		I	Complies	Cr	Max 0.20	0.081	--	--	--	
Hydrogen Content (ml/100g)		--	6.45	Ni	Max. 0.30	0.19	Fillet weld test of t-joint		Complies	
Approved Classification Grade		CCS (--)	LR (--)	GL (--)	NK (--)	ABS (--)	BV (--)	DNV (--)	KR (--)	RINA (--)
10050 NW 116TH Way, Suite 15. Medley, Florida 33178. Telf: 305-4205099				This is to certify that the welding consumable conform with the standard						
				Signature		Inspection seal				
										