



THE MOST RELIABLE WELDING®

HOFFMAN ARC CO., LTD

QUALITY CERTIFICATE OF WELDING CONSUMABLE

Type	Norm	Brand Name	Part #	Diameter	Lot No.	Manufactured Date	Date of Issue
E7018	AWS A5.1/A5.1M-2004	Sinnvoll	6001802	1/8" (3.2mm)	17-1235	Shown on Package	2017 / 07 / 12

Mechanical Properties of Deposited Metal			Chemical Composition of Deposited Metal (%)							
Item		Requirement	Actual Result	Element	Requirement	Actual Result	Element	Requirement	Actual Result	
Yield Strength Rel(MPa)		--	511	C	≤ 0.15	0.075	Mo	≤ 0.30	0.002	
Tensile Strength Rm(MPa)		--	604	Si	≤ 0.75	0.58	V	≤ 0.08	0.014	
Elongation A5 (%)		--	23.5	Mn	≤ 1.6	1.60	Cu	--	--	
Sharp V noch	Impact Temp (°C)	--	-30	S	≤ 0.035	0.0095	A1	--	--	
	Av. Absorbed Energy (J)	--	142 138 135	P	≤ 0.035	0.019	Ti	--	--	
X-Ray		--	--	Cr	≤ 0.2	0.014	--	--	--	
Hydrogen Content (ml/130g)		--	--	Ni	≤ 0.3	0.048	--	--	--	
Approved Classification Grade		CCS (--)	LR (--)	GL (--)	NK (--)	ABS (--)	BV (--)	DNV (--)	KR (--)	RINA (--)
10050 NW 116TH Way, Suite 15. Medley, Florida 33178. Telf: 305-4205099				This is to certify that the welding consumable conform with the standard						
				Signature		Inspection seal				
				APPROVED BY LIAO YUGANG		HoffmanArc®				