



THE MOST RELIABLE WELDING®

HOFFMAN ARC CO., LTD

QUALITY CERTIFICATE OF WELDING CONSUMABLE

Type	Norm	Brand Name	Part #	Diameter	Lot No.	Manufactured Date	Date of Issue
AWS E6010	AWS A5.1/A5.1M ASME SFA-5.1/SFA-5.1M	BAUEN	6001002	1/8" (3.2MM)	25-30024	SHOWN ON PACKAGE	08 / 08 / 2025

Mechanical Properties of Deposited Metal			Chemical Composition of Deposited Metal (%)						
Item		Requirement	Actual Result	Element	Requirement	Actual Result	Element	Requirement	Actual Result
Yield Strength Rel(MPa)		≥330	412	C	≤0.2000	0.11	Mo	≤0.3000	0.0012
Tensile Strength Rm(MPa)		≥430	488	Si	≤1.0000	0.21	V	≤0.0800	0.0045
Elongation A5 (%)		≥22	24	Mn	≤1.2000	0.62	Cu	--	--
Impact Test	Impact Temp (°C)	-30	-30	S	≤0.0350	0.0075	Ti	--	--
	Impact Absorbed Energy (J)	≥27	65 58 71	P	≤0.0400	0.018	Al	--	--
X-Ray		--	Complies	Cr	≤0.2000	0.035	--	--	--
Hydrogen Content (ml/100g)		--	--	Ni	≤0.3000	0.036	Fillet weld test of T-joint		Passed
Approved Classification Grade		CCS (--)	LR (--)	GL (--)	NK (--)	ABS (--)	BV (--)	DNV (--)	KR (--) RINA (--)
10050 NW 116TH Way, Suite 15. Medley, Florida 33178. Telf: 305-4205099				This is to certify that the welding consumable conform with the standard Signature APPROVED BY LIAO YUGANG Inspection seal HoffmanArc					

