



THE MOST RELIABLE WELDING®

HOFFMAN ARC CO., LTD

QUALITY CERTIFICATE OF WELDING CONSUMABLE

Type	Norm	Brand Name	Part #	Diameter	Lot No.	Manufactured Date	Date of Issue
AWS E6010	AWS A5.1/A5.1M ASME SFA-5.1/SFA-5.1M	BAUEN	6001003	5/32" (4.0MM)	25-30017	SHOWN ON PACKAGE	09 / 05 / 2025

Mechanical Properties of Deposited Metal			Chemical Composition of Deposited Metal (%)							
Item		Requirement	Actual Result	Element	Requirement	Actual Result	Element	Requirement	Actual Result	
Yield Strength Rel(MPa)		≥330	383	C	≤0.2000	0.13	Mo	≤0.3000	0.0026	
Tensile Strength Rm(MPa)		≥430	461	Si	≤1.0000	0.14	V	≤0.0800	0.0048	
Elongation A5 (%)		≥22	23	Mn	≤1.2000	0.53	Cu	--	--	
Impact Test	Impact Temp (°C)	-30	-30	S	≤0.0350	0.0044	Al	--	--	
	Impact Absorbed Energy (J)	≥27	49 58 97	P	≤0.0400	0.012	Ti	--	--	
X-Ray		Required	Complies	Cr	≤0.2000	0.045	--	--	--	
Hydrogen Content (ml/100g)		--	--	Ni	≤0.3000	0.012	Fillet weld test of T-joint		Complies	
Approved Classification Grade		CCS (--)	LR (--)	GL (--)	NK (--)	ABS (--)	BV (--)	DNV (--)	KR (--)	RINA (--)

10050 NW 116TH Way, Suite 15.
Medley, Florida 33178.
Telf: 305-4205099

This is to certify that the welding consumable conform with
the standard
Signature



Inspection seal

